

TITLE OF THE INVENTION

Liquid Crystal Device and Manufacturing Method Therefor

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to liquid crystal device and manufacturing method for the same.

2. Description of the Prior Art

Liquid crystal devices have been broadly used. Particularly, due to their light weights and small sizes, many compact electric appliances such as compact electric calculators, watches, lap-top word processors and pocket television systems are provided with liquid crystal displays.

The driving circuit of such a liquid crystal display has been formed in a separate printed board made of a glass epoxy substrate in which a semiconductor device such as a packaged IC is mounted. The electric connection is made through FPC (Flexible Print Circuit) between the printed board and inner electrodes formed in the insides surfaces of a pair of substrates in which a liquid crystal is disposed.

Recently, TAB (Tape Automated Bonding) has been employed to make electric connection. In accordance with this method, semiconductor chips provided with solder bumps on their contact pads are mounted on and electrically connected with Cu electrodes formed on a polyimide film by face-down bonding (ILB: Inner Lead Bonding), and then electrode strips formed on the substrates of a liquid crystal display are coupled respectively with counterpart electrode strips of the polyimide film (OLB: Outer Lead Bonding).

The IC chips can be mounted directly on the substrates of a liquid crystal display. In this case, an electric circuit pattern for supplying driving signals to electrode strips of the substrates defining pixels of the liquid crystal display and control signals to the chips has to be formed in advance. The IC chips are connected to the pattern by means of Au wiring or bumps attached to the contact pads of the chips.

There are some shortcomings, however, in the above

conventional technique. In the case using a glass epoxy board, the advantage of light weights claimed by liquid crystal display is largely diminished because of the heavy board. Furthermore, the use of the intermediary FPC is undesirable. There are two sites of connection at both ends of the FPC and therefore the frequency of occurrence of connection error is doubled. The difference between the FPC and the glass substrates of a liquid crystal display in thermal expansion coefficient becomes a cause of stress at the connection. This problem is also the case at the connection made in accordance with the TAB method. In addition, polyimide tape is expensive. In the case of the direct mounting of IC chips, the yield of production is the product of the yield of liquid crystal panel and the yield of the driving circuit and therefore the decrease of the whole yield is substantial.

BRIEF SUMMARY OF THE INVENTION

It is an object of the present invention to provide a light weight liquid crystal device.

It is another object of the present invention to provide a method of manufacturing liquid crystal devices at a high yield.

Additional objects, advantages and novel features of the present invention will be set forth in the description which follows, and in part will become apparent to those skilled in the art upon examination of the following or may be learned by practice of the present invention. The object and advantages of the invention may be realized and attained by means of the instrumentalities and combinations particularly pointed out in the appended claims.

To achieve the foregoing and other object, and in accordance with the present invention, as embodied and broadly described herein, there is provided a third substrate beside a pair of substrates sandwiching a liquid crystal layer therebetween. The third substrate is provided with IC chips for producing driving signals to be supplied to electrode arrangement formed on the inside surfaces of the pair of substrates. In accordance with the present invention, no epoxy print board is used and therefore

the peculiar advantage of liquid crystal devices, i.e. the light weight, is not diminished.

As a method for electrically connecting the third substrate and the pair of substrates, there are several examples such as a method making use of a UV light curable anisotropic conductive adhesive disposed between the third substrate and the respective substrates, a method making use of FPCs or a method making use of an anisotropic conductive rubber.

Furthermore, in accordance with the present invention, the liquid crystal panels and the circuit boards for producing driving signals are manufactured and tested separately and therefore inoperative boards can be eliminated in advance of assembling process of liquid crystal displays so that the yield is expected to substantially increase.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are incorporated in and form a part of the invention and, together with the description, serve to explain the principles of the invention.

Fig.1 is a perspective view showing a liquid crystal display in accordance with an embodiment of the present invention.

Figs.2(A) and 2(B) are plan views showing substrates formed with electrode strips for liquid crystal display.

Fig.3 is a partial cross sectional view showing electrical connection between substrates carrying electrode strips in accordance with the present invention.

Fig.4 is a perspective view showing a liquid crystal display in accordance with a modification of the embodiment of the present invention shown in Fig.1.

Fig.5 is a perspective view showing a liquid crystal display in accordance with another modification of the embodiment of the present invention.

Fig.6 is a perspective view showing a liquid crystal display in accordance with a further modification of the embodiment of the present invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Referring now to Figs. 1, 2 and 3, a liquid crystal display in accordance with the present invention is illustrated. The liquid crystal display comprises a pair of glass substrates 1 and 2 between which a liquid crystal layer is disposed, and a pair of auxiliary substrates 3 carrying thereon a driving circuit for supplying driving signals to orthogonal electrode strips 9 arranged in the inside surfaces of the substrates 1 and 2 as shown in Fig. 1. The auxiliary substrates 3 and the substrates 1 and 2 are connected respectively at their edges in order to establish electrical coupling between corresponding electrodes.

Next, a method of manufacturing the liquid crystal display in accordance with a first embodiment is explained. First and second sodalime glass substrates of 1.1 mm thickness are coated with transparent conductive films such as ITO (Indium Tin Oxide) films by DC magnetron sputtering to a thickness of 1200 angstroms. The conductive films are patterned by means of laser pulses emitted from an excimer laser into a number of parallel electrode strips as shown in Fig. 2(A). The number of electrode strips of the first substrate is 640 while that of the second is 400 since the shape of the substrates is rectangular and the electrode strips have to be orthogonally arranged when the substrates are joined in order to define pixels therebetween at the intersections of the orthogonal strips. The output energy of the excimer laser beam is 250 mJ. The pulse width is 20 nanoseconds. The cross section of the beam is 15 μ m x 400 mm. The repetition frequency is 10 Hz.

The laser scribing is carried out in the same manner again for the purpose of insuring the insulation between adjacent terminals of the electrodes. Namely, after the electrodes are formed, the laser scribing is carried out in order to reduce the width of the ends of the electrodes as shown in Fig. 2(B) with a mask covering the center portions thereof. The cross section of the excimer laser beam in this case is 30 μ m x 400 mm. The other lasing conditions are same as those of the above. The surfaces of

the substrates provided with the electrodes are then coated with polyamic acid by the offset printing. The polyamic acid is then cured in a clean oven at 350 °C for three hours to form polyimide thin films. The polyimide film on the first substrate is given rubbing treatment by means of a cotton cloth and SiO₂ fine particles of 8 μm diameter are dusted thereon as spacers. The second substrate is given an adhesive at its perimeter and joined to the first substrate. The inside space between the first and second substrates are filled with a liquid crystal material by a known vacuum injection. The opening, through which the liquid crystal material is injected, is then sealed off by an adhesive cured by ultraviolet rays. One side of each of the first and second substrates extends together with the electrode strips and is exposed beyond the other substrate in order to provide contacts for electrically connection with the driving circuits formed on the auxiliary substrates 3 as shown in Fig.1.

The auxiliary substrates 3 are provided by depositing ITO films on 1.1 mm thick sodalime glass substrates of 50 mm width and 270 mm length. The ITO film is patterned by a known photolithography. The ITO pattern is then coated with Ni and thereafter with Au respectively by plating. The pattern includes contacts with which IC chips for producing driving signals are electrically connected. The connection of the chips and the contacts are made by applying Au bumps to contact pads of the chips, dripping a curable adhesive onto the rare surfaces of the chips and, after aligning the pads and the contacts of the substrate, exposing the adhesive to ultraviolet light under pressure of 95g per bump at 150 °C for three minutes in order to harden the adhesive and fix the chips to the substrate. Then, the driving circuits as manufactured as above on the substrate are tested at the outer leads with which the electrodes of a liquid crystal display should be connected for supplying driving signals in order to eliminate substrates carrying inoperative circuits.

The electric connection between the first and second substrates 1 and 2 and the counterpart auxiliary substrates 3

respectively are done as follows. The extended inside surfaces of the first substrates 1 on which terminals of the respective electrodes are exposed are coated, by means of a dispenser, with an anisotropic conductive film. The adhesive film is made from a UV light curable adhesive 8 in which a number of resilient fine conductive particles 6 and hard particles 7 whose diameter is slightly smaller than that of the resilient particles are dispersed. The resilient particles are made from 7.5 μm thick polystyrene spheres plated with a 1000 angstroms thick Au film. The hard particles are made from 5 μm thick SiO_2 spheres. The weight proportion among the adhesive, the resilient particles and the hard particles is 107:14:1. Then, the first substrate 1 and the auxiliary substrates 3 are joined with the adhesive therebetween in order that the terminals of the first substrate 1 and the corresponding contacts of the auxiliary substrate 3 are aligned to each other, and exposed to UV light for 3 minutes under pressure of about 2.4 kg/cm^2 . The hard particles are included in order to prevent the conductive resilient particles from being destroyed under excess pressure. The second substrate 2 is electrically connected with the other auxiliary substrate 3 in the same manner. When displays as produced as above were subjected to a thermal shock test at -30°C and at 70°C respectively for an hour, all the sample displays were maintained operatable.

Next, a method of manufacturing the liquid crystal display in accordance with a second embodiment is explained in conjunction with Figs. 1, 2(A) and 3. First and second sodalime glass substrates of 1.1 mm thickness are coated with transparent conductive films such as ITO (Indium Tin Oxide) films by DC magnetron sputtering to a thickness of 1200 angstroms. The conductive films are patterned by means of laser pulses emitted from an excimer laser into a number of parallel electrode strips as shown in Fig. 2(A). The number of electrode strips of the first substrate is 640 while that of the second is 400 since the shape of the substrates is rectangular and the electrode strips have to be orthogonally arranged when the substrates are joined in order

to define pixels therebetween at the intersections of the orthogonal strips. The output energy of the excimer laser beam is 250 mJ. The pulse width is 20 nanoseconds. The cross section of the beam is 15 μm x 400 mm. The repetition frequency is 10 Hz.

In this case, the treatment of terminals of the electrode strips 9 is not carried out. A liquid crystal panel is assembled in the same manner as the above embodiment except that the first and second substrates are provided with the electrode strips as illustrated in Fig.2(A) rather than Fig.2(B). A pair of auxiliary substrates are provided also in the same manner as the above embodiment.

The electric connection between the first and second substrates 1 and 2 and the counterpart auxiliary substrates 3 respectively are done as follows. The extended inside surfaces of the first substrates 1 on which terminals of the respective electrodes are exposed are coated, by means of a dispenser, with an anisotropic conductive film. The adhesive film is made from a UV light curable adhesive 8 in which a number of resilient fine conductive particles 6 and hard particles 7 whose diameter is slightly smaller than that of the resilient particles are dispersed. The resilient particles are made from 2.5 μm thick polystyrene spheres plated with a 1000 angstroms thick Au film. The hard particles are made from 2 μm thick SiO_2 spheres. The weight proportion among the adhesive, the resilient particles and the hard particles is 98:13:3. Then, the first substrate 1 and the auxiliary substrates 3 are joined with the adhesive therebetween in order that the terminals of the first substrate 1 and the corresponding contacts of the auxiliary substrate 3 are aligned to each other, and exposed to UV light for 3 minutes under pressure of about 2.4 kg/cm². The hard particles are included in order to prevent the conductive resilient particles from being destroyed under excess pressure. The second substrate 2 is electrically connected with the other auxiliary substrate 3 in the same manner. When displays as produced as above were subjected to a thermal shock test at -30 $^{\circ}\text{C}$ and at 70 $^{\circ}\text{C}$ respectively for an hour, all the

sample displays were maintained operatable.

Next, a method of manufacturing the liquid crystal display in accordance with a third embodiment is explained in conjunction with Figs.1 and 2(A). First and second sodalime glass substrates of 1.1 mm thickness are coated with transparent conductive films such as ITO (Indium Tin Oxide) films by DC magnetron sputtering to a thickness of 1200 angstroms. The conductive films are patterned by a known photolithography into a number of parallel electrode strips as shown in Fig.2(A). The number of electrode strips of the first substrate is 640 while that of the second is 400 since the shape of the substrates is rectangular and the electrode strips have to be orthogonally arranged when the substrates are joined in order to define pixels therebetween at the intersections of the orthogonal strips.

The surfaces of the substrates provided with the electrodes are then coated with polyamic acid by the offset printing. The polyamic acid is then cured in a clean oven at 350 °C for three hours to form polyimide thin films. The polyimide film on the first substrate is given rubbing treatment by means of a cotton cloth and SiO₂ fine particles of 8 µm diameter are dusted thereon as spacers. The second substrate is given an adhesive at its perimeter and joined to the first substrate. The inside space between the first and second substrates are filled with a liquid crystal material by a known vacuum injection. The opening, through which the liquid crystal material is injected, is then sealed off by an adhesive cured by ultraviolet rays. One side of each of the first and second substrates extends together with the electrode strips and is exposed beyond the other substrate in order to provide contacts for electrically connection with the driving circuits formed on the auxiliary substrates 3 as shown in Fig.1. Then, a pair of auxiliary substrates are provided, tested and coupled with the liquid crystal panel in the same manner as the above embodiment.

Fig.4 illustrates a modification of the embodiment illustrated in Fig.1. The liquid crystal panel is same as that of

Figure 1 displays 11 bar charts comparing the percentage of respondents in various demographic and attitudinal categories for the Control group (white bars) and the Treatment group (black bars). The categories are: Age, Sex, Education, Income, Marital Status, Religion, Political Party, Country of Birth, Country of Residence, Length of Residence, and Country of Birth.

Variable	Category	Control (%)	Treatment (%)
Age	18-24	15	15
	25-34	25	25
	35-44	30	30
	45+	30	30
Sex	Male	50	50
	Female	50	50
Education	Less than High School	15	15
	High School	35	35
	Some College	25	25
	College or More	25	25
Income	Less than \$10,000	15	15
	\$10,000-\$20,000	30	30
	\$20,000-\$30,000	25	25
	\$30,000+	30	30
Marital Status	Married	50	50
	Single	50	50
Religion	Protestant	50	50
	Catholic	50	50
Political Party	Democrat	50	50
	Republican	50	50
Country of Birth	U.S.	50	50
	Foreign	50	50
Country of Residence	U.S.	50	50
	Foreign	50	50
Length of Residence	Less than 1 year	15	15
	1 year or more	85	85
Country of Birth	U.S.	50	50
	Foreign	50	50

Figure 1 displays 11 bar charts comparing the percentage of respondents in various demographic and attitudinal categories for the Control group (white bars) and the Treatment group (black bars). The categories are: Age, Sex, Education, Income, Marital Status, Religion, Political Party, Country of Birth, Country of Residence, Length of Residence, and Country of Birth.

Variable	Category	Control (%)	Treatment (%)
Age	18-24	15	15
	25-34	25	25
	35-44	30	30
	45+	30	30
Sex	Male	50	50
	Female	50	50
Education	Less than High School	15	15
	High School	35	35
	Some College	25	25
	College or More	25	25
Income	Less than \$10,000	15	15
	\$10,000-\$20,000	30	30
	\$20,000-\$30,000	25	25
	\$30,000+	30	30
Marital Status	Married	50	50
	Single	50	50
Religion	Protestant	50	50
	Catholic	50	50
Political Party	Democrat	50	50
	Republican	50	50
Country of Birth	U.S.	50	50
	Foreign	50	50
Country of Residence	U.S.	50	50
	Foreign	50	50
Length of Residence	Less than 1 year	15	15
	1 year or more	85	85
Country of Birth	U.S.	50	50
	Foreign	50	50

Figure 1 displays 11 bar charts comparing the percentage of respondents in various demographic and attitudinal categories for the Control group (white bars) and the Treatment group (black bars). The categories are: Age, Sex, Education, Income, Marital Status, Religion, Political Party, Country of Birth, Country of Residence, Length of Residence, and Country of Birth.

Variable	Category	Control (%)	Treatment (%)
Age	18-24	15	15
	25-34	25	25
	35-44	30	30
	45+	30	30
Sex	Male	50	50
	Female	50	50
Education	Less than High School	15	15
	High School	35	35
	Some College	25	25
	College or More	25	25
Income	Less than \$10,000	15	15
	\$10,000-\$20,000	30	30
	\$20,000-\$30,000	25	25
	\$30,000+	30	30
Marital Status	Married	50	50
	Single	50	50
Religion	Protestant	50	50
	Catholic	50	50
Political Party	Democrat	50	50
	Republican	50	50
Country of Birth	U.S.	50	50
	Foreign	50	50
Country of Residence	U.S.	50	50
	Foreign	50	50
Length of Residence	Less than 1 year	15	15
	1 year or more	85	85
Country of Birth	U.S.	50	50
	Foreign	50	50

Figure 1 displays 11 bar charts comparing the percentage of respondents in various demographic and attitudinal categories for the Control group (white bars) and the Treatment group (black bars). The categories are: Age, Sex, Education, Income, Marital Status, Religion, Political Party, Country of Birth, Country of Residence, Length of Residence, and Country of Birth.

Variable	Category	Control (%)	Treatment (%)
Age	18-24	15	15
	25-34	25	25
	35-44	30	30
	45+	30	30
Sex	Male	50	50
	Female	50	50
Education	Less than High School	15	15
	High School	35	35
	Some College	25	25
	College or More	25	25
Income	Less than \$10,000	15	15
	\$10,000-\$20,000	30	30
	\$20,000-\$30,000	25	25
	\$30,000+	30	30
Marital Status	Married	50	50
	Single	50	50
Religion	Protestant	50	50
	Catholic	50	50
Political Party	Democrat	50	50
	Republican	50	50
Country of Birth	U.S.	50	50
	Foreign	50	50
Country of Residence	U.S.	50	50
	Foreign	50	50
Length of Residence	Less than 1 year	15	15
	1 year or more	85	85
Country of Birth	U.S.	50	50
	Foreign	50	50

principles of the invention and its practical application thereby to enable others in the art to utilize most effectively the invention in various embodiments and with various modifications as are suited to the particular use contemplated. Although in the above description a pair of substrates sandwiching a liquid crystal layer are provided with electrode strips and connected with a pair of auxiliary substrates on which IC chips are mounted respectively to supply driving signals there are devices which require driving signals only at one of the pair of the substrates. In this case, the auxiliary substrates are needed only one for one liquid crystal panel.